

CRYO-BOND 877 CRYOGENIC ADHESIVE

Product Description

CRYO-BOND 877 is a 100 percent solids, three-component cryogenic adhesive.

CRYO-BOND 877 is formulated in a convenient 40 Lb. kit one to-one mixing ratio. It may be used as part of a system with other Valpac elastomeric coatings.

Features/Typical Properties

Solids Volume (Calculated)	100%
Coverage Range	1/16 inch - 68 sq. ft. 1/8 inch 34 sq. ft. 1/4 inch 17 sq. ft.
Mix Ratio	Pre-measured kit
Weight (ASTM D-1475)	15.5 pounds +/- 0.5 pounds/ Gallon (mix) Total Mix = 2.6 gallons or
Shelf Life 30°F (-10°C) 85°F (29°C)	1 year
Flash Point Tag Closed Cup	Greater than 250° F
Service Temperature Limits	-320° F to 250° F (-196° C to 121° C)
Color	Black Only

- Very low permeability
- Good chemical resistance
- High build
- · Convenient mixing ratio

Recommended Uses

CRYO-BOND 877 is designed for use over polyurethane foam and other substrates where a coating with low permeability is required, such as cryogenic systems.

CRYO-BOND 877 is compatible with most Valpac finish coat elastomers. For other compatible coatings, contact Valpac's technical staff.

Specification Data

Ordering Information

Packaging:	40 Lb. kits	
3	kits: 40 Lbs (Net)	
Shipping Weight:	45 Lbs. (Gross)	
Freight Classification:	Coating Solution, Flammable	
	Liquid UN1139, Freight_Class 55	

<u>Method</u>: Cryo-Bond 877 should only be applied by notched trowel to thoroughly cleaned dry surfaces. Suggested thickness is between 1/16 to 1/8 of an inch.

Batch Mixing: Thoroughly power agitate A & B materials until completely mixed. Add Part C (Aggregate) while continuing to mix for approximately 3 to 4 minutes until the entire mixture is uniform.

Pot Life:

MATERIAL TEI	MPERATURE	TIME
70 °F to 80 °F	(21°C to 27°C)	1 to 2 hours
90°F to 100°F	(32°C to 38°C)	1/2 hour

Safety Information:

- *Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
- *Do not apply material in enclosed areas without adequate air exchange and ventilation.
- *All application personnel must use fresh air respirators or fresh air hoods.
- *Wear protective clothing, gloves and eye protection.
- *Breathing fumes or contact with the skin may cause severe allergic reactions.
- *This product is intended for industrial use by properly trained professional applicators only.

<u>Clean-Up:</u> Must be cleaned before it cures. Use a mineral spirits (flammable) or chlorinated solvent non-flammable).

Application Guidelines:

1. Do not apply over wet or contaminated substrates or when inclement weather is imminent.

Cure Times:

The curing rate will vary depending on film thickness, ambient air and substrate temperatures and humidity.

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any invention or existing patent without a license.

Valpac, Inc.
Construction Products Division
1400 Industrial Park Road
Federalsburg, MD 21632

Tel: 410-754-7390

□ www.valpac.com □

Fax: 410-754-7541